CX3399741 | 1250135WP1250TAPE COEX

ConQuest® Empty Conduit, 1 1/4 in, SDR 13.5, orange, with pull tape



| Product Classification | |
|----------------------------|--|
| Product Type | Empty conduit |
| Product Brand | ConQuest® |
| General Specifications | |
| Color | Orange |
| Conduit Type | Non-toneable |
| Density Test Method | ASTM D792A |
| Density, maximum | 0.955 g/cm ³ 0.035 lb/in ³ |
| Density, minimum | 0.941 g/cm ³ 0.034 lb/in ³ |
| Design Standard | ASTM D3350-05 |
| Wall Type | Smooth |
| Dimensions | |
| Length | 914.4 m 3000 ft |
| Inner Diameter, nominal | 35.408 mm 1.394 in |
| Outer Diameter, nominal | 42.164 mm 1.66 in |
| Wall Thickness Designation | SDR 13.5 |
| Wall Thickness, minimum | 3.124 mm 0.123 in |
| Nominal Size | 1-1/4 in |
| Material Specifications | |

Material Specifications

| Flexural Modulus, minimum | 551.581 N/mm ² 80000 psi |
|-------------------------------|---------------------------------------|
| Flexural Property Test Method | ASTM D790 |
| Hydrostatic Design Basis | Not pressure rated |

Page 1 of 2

©2020 CommScope, Inc. All rights reserved. All trademarks identified by ® or [™] are registered trademarks, respectively, of CommScope. All specifications are subject to change without notice. See www.commscope.com for the most current information. Revised: November 6, 2020



CX3399741 | 1250135WP1250TAPE COEX

| Hydrostatic Design Test Method | ASTM D2837 |
|--------------------------------|--|
| Material Type | High density polyethylene (HDPE) Polyester |
| Melt Flow Rate Test Method | ASTM D1238 |
| Melt Flow Rate, maximum | 0.39 g/10 min |

Mechanical Specifications

| Minimum Bend Radius, unsupported | 457.2 mm 18 in |
|------------------------------------|-------------------------|
| Tensile Property Test Method | ASTM D638 |
| Tensile Strength at yield, minimum | 20.684 N/mm² 3000 psi |
| Breaking Strength | 566.99 kg 1250 lb |
| Pull Line Type | Таре |
| Pulling Tension, maximum | 571.526 kg 1260 lb |

Environmental Specifications

| Environmental Stress Crack Resistance | Failure rate of 10% within 96 hours |
|---------------------------------------|-------------------------------------|
| Environmental Stress Test Method | ASTM D1693, ESCR Condition B |

Packaging and Weights

Weight, net

394.363 kg/km | 265 lb/kft

Regulatory Compliance/Certifications

Agency

Classification

ISO 9001:2015

Designed, manufactured and/or distributed under this quality management system



* Footnotes

Environmental Stress Crack Resistance ESCR-Environmental Stress Crack Resistence

Page 2 of 2

